



P 962 1K ISOLATOR PRIMER

Technical Data Sheet No 130

VOC compliant with the regulations

One component air drying system

New generation primer suitable for metallic and wooden surfaces

Dries quickly

P 962 1K ISOLATOR prevents lifting and bleeding of existing old paint films, sensitive to strong solvents.

General Technical Description



Non Force dry
1h / 23°C (73°F)

Surface

Adhesion to any coated surface

Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL/ BODY 771 ANTISIL FAST

Use P 400 for wet sanding, re-clean the surface and dry thoroughly

Use P 180 for sanding on applications direct to metals



Make sure you always use appropriate face protection and good ventilation

Product Application:

»» Apply 1 coat on any coated surface. Make sure there is a uniform coverage on the applied surface.



P 962 1K ISOLATOR is ready for use.



P 962 1K ISOLATOR SHOULD NOT BE SANDED BEFORE THE APPLICATION OF ANY OTHER COATS OF PRIMER

Flash Point:
15°C / 59°F

Remarks:

- It can be used by countries that do not adopt the VOC legislation as well.



Ready to spray:
20-25 s
DIN 4 @ 20°C (68°F)



Over coat with:
HB BODY PRIMERS

Specific Gravity:
1.1 g/cm³

- Clean all the equipment with any alcohol based solvents such as BODY 769 Gun Wash Cleaner, in order to avoid any product remains in the spray gun



Do not add thinner (Reducer)



Store in a cool place

Solid Content (No thinner):
48% Weight

- Make sure you stir well and filter the product before every use. Do NOT overload, P 962 ISOLATOR when applying. Always check that the air line is free of moisture.



HVLP Spray gun
1.4m - 1.8 mm
2 bar (29psi)
atomization pressure
1 coats = 20µm (0.8mil)
(recommended)



Always wear protective equipment

VOC (2004/42/EC)
This is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 540 g/L. The VOC content in the ready for use form of this product is 535 g/L.
2004/42/IIIB(c)(540)535

Storage Shelf life:

- Store in a cool place (+5°C to 25°C) (41°F - 77°F) and use within 12 months for best results. Guaranteed shelf life of 18 months in unused original containers.



Allow 5 - 10 minutes between coats (if second coat is needed)



Follow the application instructions mentioned in this TDS

Theoretical Coverage:
12-15 m² / l at 20 micron (0.8mil) dry film thickness

Cleaning of equipment:
Clean after final use with BODY 769 Gun wash Cleaner



Non force dry
1 h / 23°C (73°F)

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The SPECIAL REFINISHING PRODUCT. 1K ACRYLIC MAT PRODUCT intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and/or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 6 / 2018, February 2018