

955 TOUGH LINER - TINTABLE

Technical Data Sheet No 722



General Description

HB BODY 955 TOUGH LINER TINTABLE, is tinted with HB BODY COLOR SOLUTIONS 2K OR BASECOAT SYSTEM. It is a protective 2K polyurethane coating to be used as a top coat on surfaces with high mechanical demands. Cured product provides impact and scratch resistance, sound proof properties, weather & UV resistance, protection against a wide range of chemicals, like hydraulic oils, fuels, animal residues, salt water and other.

Surface

All metallic surfaces
 Plastic
 Old 2K paint work
 OEM
 Wood
 Polyester unsanded fiberglass
 HB BODY 955 TOUGH LINER can be applied on most surfaces without primer. For maximum adhesion and anticorrosion properties on bare metal it is recommended prior use of HB BODY 989 4:1 EPOXY PRIMER or P 961 1K ETCH PRIMER.

Pretreatment / Cleaning of substrate



Surface must be lightly sanded (P100 - P180). Clean surface from dirt, oil or grease using a soft cloth and 770 ANTISIL NORMAL / 771 ANTISIL FAST DEGREASER.



Make sure you always use appropriate protection.

Product Application:



Mix ratio 3 parts
 A. 955 TOUGH LINER TINTABLE
 1 part B. 955 HARDENER



30min / 60°C (140°F)
 Light duty 1 - 2 days
 Fully cured 3 - 4 days

Flash Point:
 9°C / 48°F

Specific Gravity:
 1.30 g/cm³

Cleaning of equipment:
 Clean after final use with:
 740 ACRYL NORMAL THINNER /
 767 ECO THINN NITRO THINNER



Add 10% of BODY 2K or Basecoat in part A. Mix with hardener and allow to stand for 10min @ 23°C (73°F)



Non force dry / 23°C
 Touch free 1h
 Light duty 2 - 3 days
 Fully cured 5 - 7 days

Solid Content (No thinner):
 67% Weight

VOC (2004/42/EC)
 This product is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 390 g/L.
 2004/42/II(B)(e)(840)390

Remarks:

- Do not use IR for fast curing.
- Best results when used with HB BODY PRODUCTS.



After mixing shake well for 2-3 min
 Pot life: 1.5h @ 23°C (73°F)



Always wear protective equipment

- It can be used by countries that do not adopt the VOC legislation as well.
- Coverage and hiding when using BODY 955 Tintable may vary, depending the colour to be used.



Flash off time
 20min / 23°C (73°F)



Follow the application instructions mentioned in this TDS

Theoretical Coverage:
 3 m² / l of mixture, applied with UBS gun 3-4 bar (44-58 psi)
 2 full coats

Storage shelf life:

- Store in a cool place +5°C - +25°C (41°F - 77°F) and use within 12 months for best results. Guaranteed shelf life of 24 months in unused original containers.

Anti - Slip Additive:



Get the maximum anti-slip effect by applying the coarse texture with UBS gun



Mix thoroughly

Remarks:

- In accordance with EN 13036-4 (BS 7976-2)
- The Anti-Slip additive might be visible after application depending on the shade



Recommended dose
 120g in 800ml of ready mixed 955 tough liner.



Can not be used with HVLP gun

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 6 / 2019, March 2019



955 TOUGH LINER - TINTABLE


Technical Data Sheet No 722

Product Application:




Standard texture with UBS gun.

- 3-4 bar (44-58 psi)
- Distance from object 50cm
- 2 coats with an even sweeping motion (30 minutes between coats at 23°C)



Coarse texture with UBS gun

- 3-4 bar (44-58 psi)
- Distance from object 50cm
- 1st coat even sweeping motion,
- 2nd coat reduce pressure 1,5 bar (22 psi)
- dropping over the first coat (30 minutes between coats at 23°C)
- **For maximum Anti-Slip effect use 955 Tough Liner Anti-Slip additive only with this texture**



Standard texture with HVLP gun (1,6 - 2,0mm)

- add 10% thinner 740
- 2 bar (29 psi)
- Distance from object 20cm
- 2 coats with an even sweeping motion as wet on wet application (30 minutes between coats at 23°C)



Coarse texture with HVLP gun (1,6 - 2,0mm)

- add 10% thinner 740
- 2 bar (29 psi)
- Distance from object 20cm
- 1st coat even sweeping motion,
- 2nd coat reduce pressure 1 - 1,5 bar (15-22 psi),
- reduce material flow to achieve fine mist.
- (30 minutes between coats at 23°C)



For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 6 / 2019, March 2019